



Matchmate NP10

Cobalt-based dental metal-ceramic material

Type 4 Nickel & Beryllium Free

Instructions for Use

INTRODUCTION

Matchmate NP10 is a highly corrosion resistant nickel and beryllium free cobalt chromium-tungsten alloy, suitable for producing metal frameworks for bonding to porcelain. It is supplied in ingots Ø8mmx15mm. The oxide produced provides an exceptionally strong metal-ceramic bond. It is manufactured in accordance with EN ISO 22674:2016.

INDICATIONS

Production of metal frameworks for veneering with bonding porcelain.

CONTRA INDICATIONS

Some electrochemical reactions or allergies may rarely occur caused by one or more elements of this alloy. Patients or users who have or are exhibiting such sensitivity should avoid using this alloy. If the instructions are observed during the production processes, incompatibilities with CoCr alloys are extremely rare. In case of a proven allergy to an ingredient of this alloy, the alloy must not be used for safety reasons. When different alloy groups are used, galvanic effects might occur. Please inform your dentist regarding the contra-indications and side effects. Any serious incident that involves the product must be reported to the manufacturer and the competent authority in the accorded country.

TYPICAL CHEMICAL COMPOSITION

Cobalt	61.65%
Chromium	27.75%
Tungsten	8.45%
Silicon	1.61%
Manganese	0.25%
Iron	0.2%
Other elements	<0.1%

WAXING

The wax pattern should be modelled with wax that burns out without residue, be designed without any sharp angles and provide an even thickness of porcelain. The pattern should be waxed-up so that the final wall thickness of the framework is at least 0.4mm after finishing.

SPRUEING

Use the usual sprueing techniques. For indirect sprueing of larger or heavy castings use a 4-5mm diameter transverse sprue bar. This may be directly

placed on the sprue cone or fed by 3-4mm diameter sprues from the cone to the bar.

When sprueing from the bar to the crowns, use sprue of 2.5-3mm diameter and 3mm length. Use direct technique for smaller bridges or single crowns with sprue of 3.5mm diameter and length 15-20mm. Correct model design and sprueing will complete efficient filling of the mould and avoid suck-back during solidification and consequent shrinkage porosity.

INVESTING & BURNOUT

Use a high carbon free ceramic investment such as Schottlander Rapicast and follow the manufacturer's recommendations for this type of alloy. When using Rapicast the temperature should be raised to 900°C and the hold temperatures specified for different size rings should be followed.

MELTING & CASTING

Matchmate NP10 should be melted in a clean, preheated, contamination free ceramic crucible. Never use graphite crucibles or inserts.

Maximum temperature for casting 1518°C.

FLAME MELTING

Use oxygen/propane in the ratio 2:1. Use a neutral adjusted flame to prevent over-heating of the alloy. Follow the manufacturer's instructions for casting machine settings. Do not use flux. Place new ingots in the pre heated crucible, move the flame in a circular motion over the ingots. Keep flame directed at ingots during melting. Start the casting procedure once the melting ingots have slumped and the melting becomes easier due to the flame pressure.

CARE: Do not allow the oxide skin to burst as this may lead to the loss of trace elements in the alloy.

HIGH FREQUENCY INDUCTION

Follow the instructions of the machine manufacturers. Start the casting cycle once all the ingots have slumped and the last "shadow" has run over the ingot.

CARE: Cast before the oxide skin bursts as this may lead to the loss of trace elements in the alloy.

RE-MELTING

Recommendation – always use new alloy.

The re-melting of sprues and buttons is not recommended because with repeated re-melting the concentration of trace elements decreases leading to a reduced metal/ceramic bond.

DE-VESTING AND TRIMMING

De-vest and then trim with tungsten carbide burs or aluminium oxide stones recommended for non precious alloys. The wall thickness should not be less than 0.3mm. Separate rotary instruments must be used for each alloy type. Grind in one horizontal direction only. It is recommended to sandblast with 110 micron aluminium oxide and 3-4 bar pressure.

PORCELAIN APPLICATION

Matchmate NP10 is compatible with enliven MC, Matchmaker MC and most other feldspathic bonding porcelains. The highest recommended firing temperature is 1000°C.

Prepare for porcelain application as follows: Degas for 10 minutes at 980°C in air (no vacuum). Sandblast with 250 micron aluminium oxide at 3-4 bar pressure. Clean as usual with distilled water in an ultrasonic bath or steam clean.

A pickling bath should never be used.

Apply the Opaque according to the manufacturer's instructions. A normal cooling cycle may be used. Matchmaker CTE Buffer may be used if required to control the oxide formation. Do not plate with gold or other precious metals.

For all porcelain firing cycles other than opaque the work should be slow cooled.

SOLDERING

Matchmate NP10 should be soldered with gold or palladium solder. It is also optimised for laser welding without carbide precipitation.

FINAL CLEANING

It is preferable to carry out final cleaning of finished work using an ultrasonic rather than a steam cleaner so as to avoid thermal shock.

TYPICAL PHYSICAL PROPERTIES

Yield strength	0.2%	375 MPa
Hardness		285 HV 10/30
Density		8.55 g/cm ³
Elongation		14.7 %
E-modulus		240 GPa
CTE (25-500°C)		14.5 x 10 ⁻⁶ K ⁻¹
Melting range		1345 - 1385 °C
Max Firing temperature		980 °C
Tensile strength		525 MPa
Corrosion resistance		<200 µg/cm ²
Tarnish resistant		Yes

HEALTH & SAFETY



The metal vapour and dust are harmful to health. Dust extraction and a respirator FFP3 according to BS EN 149 should be used.



Refer to Safety Data Sheet.

STORAGE

Temperature, humidity or light has no effect on the product properties.

DISPOSAL INSTRUCTIONS

Consult the material safety data sheets or national regulations for disposal. Dispose of NP10 residues and dust in an environmentally friendly manner. Grinding dust must not enter groundwater, water bodies or sewers. Address waste exchanges for recycling.

LOT NUMBERS

The Lot number is shown on the outside of all containers.

This product is specifically formulated for use in dentistry.

Matchmate is an internationally registered trade mark of Davis Schottlander & Davis Limited.

